

CellAdhere™ Type I Collagen, Aligned-Crimped Slides

3D-oriented matrix structure for cell migration and proliferation studies

Catalog # 07007

6 Slides



Scientists Helping Scientists™ | WWW.STEMCELL.COM

TOLL FREE PHONE 1 800 667 0322 • PHONE +1 604 877 0713

INFO@STEMCELL.COM • TECHSUPPORT@STEMCELL.COM

FOR GLOBAL CONTACT DETAILS VISIT OUR WEBSITE

Product Description

CellAdhere™ Type I Collagen, Aligned-Crimped Slides is an engineered scaffold consisting of Type I Collagen deposited on the surface in a specific manner using a highly controlled process (Vrana et al.; Besseau et al.); the purified collagen is printed onto borosilicate glass chips using Fibralign™ Nanoweave™ technology at a thickness of about 1 µm while aligning the collagen fibrils in an exact orientation. As the aligned fibrils are applied to a glass slide, the process is controlled for parameters such as fibril positioning, mechanical strength, structural uniformity, average fibril sizes, and optical characteristics. The crimped configuration is intended to closely mimic the organization of collagen fibril bundles found in heart, ligament, and tendon tissues.

CellAdhere™ Type I Collagen, Aligned-Crimped is provided on 8 x 15 mm glass slides. The label “UP” on the slide indicates the side on which the aligned collagen matrix is provided. This product is recommended for cell culture applications requiring highly reproducible cell orientation, cell migration studies, and cell-extracellular matrix interaction studies.

Properties

Storage: Store at 15 - 25°C.

Shelf Life: Stable for 12 months from date of receipt.

Handling / Directions For Use

PREPARING SLIDES FOR CELL CULTURE

1. Remove CellAdhere™ Type I Collagen, Aligned-Crimped Slide from container using sterile forceps. Do not disrupt the matrix on the slide.

NOTE: Use the “UP” label on the slide to identify the side on which the matrix is deposited.

2. Place slide in sterile D-PBS Without Ca++ and Mg++ (Catalog #37350) for 5 minutes.
3. Remove and rinse slide in deionized water for 5 - 10 seconds.
4. Remove slide and place in sterile 70% ethanol for at least 1 hour. This step will sterilize the slide.
5. Remove slide and allow it to air dry.

NOTE: Placing the slide at an angle allows ethanol to evaporate faster.

6. Place slide in cultureware so that the “UP” label can be read.
7. Add DMEM with 1000 mg/L D-Glucose (Catalog #36253) or other serum-free culture medium to cultureware to cover the slide. For example, add 3 mL of DMEM in a 35 mm Culture Dish (Catalog #27100).

8. Incubate at 37°C for 45 minutes.

9. Aspirate medium.

10. Add cell suspension to cultureware.

NOTE: Use DMEM with 1000 mg/L D-Glucose or other serum-free basal medium to prepare cell suspension.

11. Incubate at 37°C until cells attach to slide.

12. Aspirate medium and replace with complete culture medium.

NOTE: Complete culture medium can contain serum.

References

Besseau L et al. (2002) Production of ordered collagen matrices for three-dimensional cell culture. *Biomaterials* 23(1): 27–36.

Vrana E et al. (2008) Contact guidance enhances the quality of a tissue engineered corneal stroma. *J Biomed Mater Res A* 84(2): 454–63.

STEMCELL TECHNOLOGIES INC.'S QUALITY MANAGEMENT SYSTEM IS CERTIFIED TO ISO 13485. PRODUCTS ARE FOR RESEARCH USE ONLY AND NOT INTENDED FOR HUMAN OR ANIMAL DIAGNOSTIC OR THERAPEUTIC USES UNLESS OTHERWISE STATED.

Copyright © 2016 by STEMCELL Technologies Inc. All rights reserved including graphics and images. STEMCELL Technologies & Design, STEMCELL Shield Design, Scientists Helping Scientists, and CellAdhere are trademarks of STEMCELL Technologies Inc. All other trademarks are the property of their respective holders. While STEMCELL has made all reasonable efforts to ensure that the information provided by STEMCELL and its suppliers is correct, it makes no warranties or representations as to the accuracy or completeness of such information.